IN THE CLAIMS

1. (Currently Amended) A solid oxide fuel cell operating at a temperature in the range of 400-700°C, comprising;:

an anode including doped-ceria, wherein said doped-ceria is deposited by colloidal spray deposition;

an electrolyte including doped-ceria, based; and

a cathode including <u>at least one</u> cobalt iron based materials, whereby the <u>wherein</u> said fuel cell is capable of operating operates in the temperature range of 400-700°C.

- 2. (Currently Amended) The fuel cell of Claim 1, wherein said anode is composed of comprises NiO and doped-ceria.
- 3. (Currently Amended) The fuel cell of Claim 1, wherein said doped-ceria includes is doped with at least one dopants selected from the group consisting of samarium oxide, gadolinium oxide, yttria oxide, and lanthanide oxide.
- 4. (Currently Amended) The fuel cell of Claim 1, wherein said <u>anode</u>, <u>said electrolyte</u>, <u>and</u> <u>said cathode are porous</u>. <u>fuel cell includes pores created by a pore former</u>.
- Cancelled

- 6. (Currently Amended) The fuel cell of Claim 1, wherein said electrolyte comprises material selected from the group consisting of doped-ceria, doped-zirconia with a thin layer of doped-ceria, and a mixture of doped-ceria and doped-zirconia.
- 7. (Currently Amended) The fuel cell of Claim 1, wherein said electrode cathode is selected from the group consisting of (La, Sr)(Co, Fe) O₃, and (La, Ca) (Co, Fe, Mn)O₃.
- 8-10. Cancelled
- 11. (Currently Amended) The fuel cell of Claim 1, wherein the cathode of the fuel cell comprises material composed of comprises a cobalt, iron, manganese based material. formed by colloidal spray deposition.
- 12. (Currently Amended) A ceria-based solid oxide fuel cell including comprising:

 an anode containing doped-ceria, wherein said doped-ceria is deposited by colloidal spray deposition;

an electrolyte containing doped-ceria,

an electrode containing cobalt iron based materials,; and

a fuel selected from the group consisting of hydrogen, methane, methanol, propane, butane and other hydrocarbons.

13. (Original) The fuel cell of Claim 12, operating in a temperature range of 400-700°C.

- 14. (Original) The fuel cell of Claim 12, wherein said fuel is composed of hydrogen or methane, and wherein the operating temperature is about 550°C.
- 15. (Currently Amended) The fuel cell of Claim 12, wherein said fuel is hydrogen, and said fuel cell has a power output of up to 400mW/cm² at an operating temperature of 550°C.
- 16. (Currently Amended) The fuel cell of Claim 12, wherein said fuel is methane, and said fuel cell has a power output of 320mW/cm² at an operating temperature of 500°C.
- 17. (Previously Amended) The fuel cell of Claim 12, wherein said anode comprises NiO and doped-ceria.
- 18. (Original) The fuel cell of Claim 17, wherein said electrolyte additionally includes doped-zirconia.
- 19. (Previously Amended) The fuel cell of Claim 18, wherein said electrode is composed of (La, Sr)(Co, Fe) O₃ selected from the group consisting of (La, Sr) (Co, Fe)O₃ and (La, Ca) (Co, Fe, Mn) O₃.
- 20. (Original) The fuel cell of Claim 19, wherein said doped-ceria is doped with samarium oxide or gadolinium oxide.

Respectfully submitted,

	1/.1	1			Ann M. Lee
Dated:	Nov.	0	, 2003	Bv:	1000 11, 199

Ann M. Lee Registration No. 47,741

Lawrence Livermore National Lab 7000 East Avenue, L-703 Livermore, CA 94550

TEL: (925)422-6458

FAX: (925)423-2231